

## OP9013 Primer – Polyurethane Systems

OP9013 is an air drying primer which promotes the adhesion of many polyurethane resin systems to many difficult and varied substrates. This primer has been particularly successful in promoting the adhesion of polyurethane resins to neoprene and PVC.

- Primer for improving adhesion; ideal for use with neoprene and PVC
- Ideal for improving the adhesion of many resin chemistries, in particular polyurethane
- Easy to use; apply by dipping or brushing
- Maximum bond strengths can be achieved after allowing the resin to cure for 7 days

**Approvals**                      **RoHS-2 Compliant (2011/65/EU):**                      **Yes**

### Typical Properties

Appearance	Brown liquid
Boiling Point (°C)	40
Density (g/ml)	1.27
Vapour Density	2.93 (air = 1)
Solubility in Water	Reacts
VOC Content (%)	75
Evaporation Rate	1.5 (Butyl Acetate = 1)

<u>Description</u>	<u>Packaging</u>	<u>Order Code</u>	<u>Shelf Life</u>
OP9013 Primer	138ml Bulk 30ml Bulk	OP9013B138ML OP9013B30ML	12 Months 12 Months

### Directions for Use

In any application where adhesion is a prime factor, cleanliness is of the utmost importance and all substrates should be degreased using solvents such as Electrolube Ultrasolve. For optimum adhesive performance the substrate should be roughened by some method to allow the primer to key itself into the surface (suitable methods are shot blasting or sanding).

The primer is applied by dipping or brushing and is then allowed to dry for approximately 90 minutes, or until nearly tack free, before applying the resin system. Maximum bond strengths are obtained by allowing the resin/primer to cure for a period of 7 days. The above recommendations are for reference only and it is advised to carry out trials in order to ascertain the suitability of this primer to your application.

Revision 1: April 2014

#### Copyright Electrolube 2013

All information is given in good faith but without warranty. Properties are given as a guide only and should not be taken as a specification.

Electrolube cannot be held responsible for the performance of its products within any application determined by the customer, who must satisfy themselves as to the suitability of the product.

Ashby Park, Coalfield Way,  
Ashby de la Zouch,  
Leicestershire LE65 1JR  
T +44 (0)1530 419 600  
F +44 (0)1530 416 640  
BS EN ISO 9001:2008  
Certificate No. FM 32082